



40 kg / bag

Hand or machine applied spatterdash plaster is used for adherence before plastering at interior and exterior applications.

Standards comply with

TS EN 998-1

Fields of Application

- Applications with PFT, trolie (mortar spray machine) or trowel on Interior and exterior surfaces of masonry bricks, briquettes, aerated concrete blocks, concrete etc.
- Walls and ceilings

Delivery, Storage and Handling

- Bags should be kept in a dry environment on pallets to prevent direct contact with water.
- It is proposed to keep the bags horizontally on a flat surface during transportation and stocking.
- Pallets should not be exposed to direct sunlight.

General Properties

	Weight (kg)	Packaging (pcs./pallet)	Shelf Life
SERPCEMENT	40	40	12 month

Technical Properties

Reaction to fire	A1
Compressive strength 28 days (N / mm ²)	CS IV ≥ 26
Bonding strength 28 days (N / mm ²)	≥ 0,08
Capillary water absorption	W0
Thermal conductivity 10, dry λ (W / mK)	≤ 1,11 (P=%50)
Water vapour diffusion resistance (μ)	≤ 15

For quality certificates visit: <http://www.knauf.com.tr/kalitebelgeleri.asp>

For recommended price list visit: <http://www.knauf.com.tr/fiyatlistesi.asp>